

PAPER-DISPERSOL

Product Code	Color	CI No	Pigment content %	Solid content %	Fineness	PH	Fastness to Acid	Fastness to Alkali	Heat Resistance	Light-fastness		Weather resistance	
										1/1	1/25	1/1	1/25
P1104	Light yellow	PY 3	40	44-46	2	7-9	5	5	150	7	6-7	4-5	4
P1140	Mid yellow	PY 14	40	50-52	2	7-9	5	5	180	5	4-5	4-5	4
P1160	Deep yellow	PY 83	35	45-50	2	7-9	5	5	200	6-7	4	2-3	1
P3138	Red	PR 8	40	46-50	2	7-9	5	5	120	6	4	3-4	2
P3130	Red	PR 2	40	46-48	2	7-9	4	2	120	6	3-4	3-4	2
P3132	Red	PR 22	40	44-46	2	7-9	4	2	120	5	2-4	3-4	2
P3150	Red	PR 112	35	44-46	2	7-9	5	4	180	7	5	4	3
P3123	Red	PR 146	40	44-46	2	7-9	5	5	180	7	5	4	4
P3128	Red	PR 170	40	44-46	2	7-9	5	4	180	7	5	4	4
P1151	Orange	PO 13	40	48-50	2	7-9	5	4	150	7-8	7	4	3
P6250	Violet	PV 3	20	26-28	2	7-9	5	4	140	5	4	4	3
P6520	Violet	PV 23	30	40-44	2	7-9	5	5	200	7-8	7	4-5	4
P4300	Reddish blue	PB 15	40	50-52	2	7-9	5	5	200	8	8	5	5
P4382	Greenish blue	PB 15:3	45	50-52	2	7-9	5	5	200	8	8	5	5
P5369	Green	PG 7	50	54-56	2	7-9	5	5	200	8	8	5	5
P2100	Black	PBL 7	35	40-42	2	7-9	5	5	200	8	8	5	5
P2200	Black	PBL 7	45	50-52	2	7-9	5	5	200	8	8	5	5

Storage : 12 months

Application:

since 1965

上海甘墨颜料化工有限公司

SHANGHAI GGINK PIGMENTS & CHEMICALS CO., LTD

Add.: Block 88, Lane 300, Shunda Road, Nanxiang, Jiading District, Shanghai, China 201802

Tel.: +86-21-6992 0922/33 Fax : +86-21-6992 0955 E-mail : ganguink@sh163.net